**DM-700H(A,B)** For MDF Membrane



# DAEHEUNG CHEMICAL

DM-700H(A,B) is two component poly-urethane base adhesive, witch is the good workability and bonding strength, heat resistance for the PVC DECO film to MDF materials.

#### 1. Uses

- Membrane bonding for profiles of chipboard, MDF, solid wood, plywood on PVC film.
- Adhesion for PVC sheet, hard board, etc.

## 2. Characteristics

- Good initial and final bonding strength.
- Good work ability of spray.
- Cold weather and heat resistance.
- Good flexibility.

## 3. Physical properties

Properties	DM-700H(A) (Resin)	DM-700(B) (Hardener)	Reference
Main component	Urethane resin	Poly isocyanate	
Color	Clear & yellow viscous liquid	Dark brown & viscous liquid	
Solid contents	11.5±1 %	20±1 %	at 105±5℃ × 3hr
Viscosity	250~500 cps	Below 200 cps	at 20℃, BF #2, 50rpm
Mixing ratio	14	0.83	By weight
Pot life	8 hr		at 20℃
Curing time	24 hr		at 20℃
Shelf life	9months in unbroken package under dry and cool condition		

#### 4. How to use

- Remove all dirt, grease, water and rust from the bonding surface before applying
- For hand mixing, combine Part A and Part B in the correct ratio and mix thoroughly. (Mixing ratio is A:B=14:0.83 by weight.)
- Spray gun Diameter : 1.0~2.5 mm
- Press : 5~6 Kgf/cm<sup>2</sup>
- Applying amount: 150~200 g/m<sup>2</sup>

TECHNICAL DATA SHEET - DM 700H(A,B)

- Dry condition : 30 min (20~25 °C)

- Chamber temperature and press time : 120±10 °C, above 120 sec
- Use profile membrane machines.

#### 5. Caution

- Avoid direct rays of the sun and keep in cool and dry place.
- Use the adhesive within pot-life.
- Close the cap tightly after using it.
- Ventilation the room well because of containing solvent.
- Don't use except for the original purpose.

#### 6. Packaging

- DM-700H(A) [Resin]: 14kg Tin C/N
- DM-700H(B) [Hardener]: 835g PE C/N

Please contact us for further information or see Material Safety Data Sheet (MSDS) for this product.

#### DAEHEUNG CHEMICAL CO., LTD.

68, Sandan-ro 64beon-gil, Pyeongtaek-si,

Gyeonggi-do, Korea

Telephone +82-2-554-8211, +82-31-668-1424

Facsimile +82-2-554-8215, +82-31-668-1425

Website www.dhcbond.co.kr



# DAEHEUNG CHEMICAL